

# Drossbach Technical Data Sheet For Flexible Convoluted Tubing / Conduit



Data Sheet:	TD-021 "LV" Polyethylene
Revision:	1
Date:	1-Sep-09
Base Material:	Polyethylene
Material Code:	LV

***Our commitment to quality is our commitment to success***

## Product Description

Flexible convoluted tubing / conduit manufactured from a blend of Low density polyethylene and ethyl vinyl acetate resins.

## Performance Enhancers

Flame Retardant	No
UV Inhibitor	No
Heat Stabilizer	No

## Performance Characteristics

Flexibility	Excellent
Abrasion Resistance	Good
Chemical Resistance	Good
Recommended Operating Upper Temperature	+200°F (93°C)
Recommended Operating Lower Temperature	-40°F (-40°C)

Typical Physical Properties	Test Method	Value	Units
Specific Gravity/Density	ASTM D792	0.924	-
Elongation @ Break	-	-	-
Elongation @ Yield	-	-	-
Tensile Strength @ 25C	-	-	-
2% Secant Modulus	-	-	-
Flexural Modulus	-	-	-
Melting Point	-	-	-
Notched Izod Impact Test	-	-	-
Heat Deflection Temperature @66psi	-	-	-
Heat Deflection Temperature @264psi	-	-	-

## Material Certifications

Delphi / Packard	-
Ford	-
General Motors	-
Chrysler	-
ASTM	-
Underwriters Laboratory	-
FMVSS 302	-

## Notes

- (1) Drossbach does not claim or state any UV life or warranty for product manufactured with a "UV inhibitor" additive as we do not have any control over its end use environment.
- (2) All "UL" and FMVSS 302 flame ratings are for the resin used to manufacture our product, not for our end product. The ratings are created by testing standard "UL" and "FMVSS" plaque specimens, not tubing samples.
- (3) All Drossbach's products are compliant with the European Union's Directive 2002/95/EU (RoHS) and the REACH Directive.
- (4) Only product designated as **UL 94 "V0"** in the Material Certification section above can be certified as **non-Halogenated product**.
- (5) If a product is designated as flame retardant but has no material certification listed, this product is a Drossbach internally blended material blended with a flame retardant additive. It is tested to an internal flame test (DR-006) that holds no claimed warranty.



**Drossbach N.A. Inc.**  
 PO Box 2000  
 157 N. Murray St.  
 Trenton, Ontario Canada  
 K8V 6G7  
 Phone: (613) 394-4817 Fax: (613) 394-5516

**Web Site Address: <http://www.drossbach.com>**  
**Email: [info@drossbachllc.com](mailto:info@drossbachllc.com)**  
**An ISO/TS 16949 and ISO-9001**  
**Registered Company**



**Drossbach LLC**  
 1500 Commerce Drive  
 Stow, OH, 44224 USA  
 Phone: (330) 688-8460  
 Toll Free: (800) 841-5804  
 Fax: (330) 688-8465